

# ULTIC ARMOR-F™



**ULTIC ARMOR-F** improves anti-cracking, anti-radical and anti-sticking performance by a wide margin, compared to other fluoroelastomers available up until now.

Moreover, **ULTIC ARMOR-F** possesses superior purity because it contains absolutely no fillers or additives.

## General Characteristics

Color	Hardness (Shore A)	Tensile Strength (MPa)	Elongation (%)	100% Modulus (MPa)	Max. Service Temp. (°C)	Compression Set (%)
Midnight Blue	67	12.4	140	5.4	200	28

Compression Set Test Conditions : 25% Compression, 200°C, 72 hrs.

Material properties shown here are actual measurements, not standards.

## Features

- High Anti-Cracking Ability
- High Radical Resistance
- Low Metallic Impurities

## Applications

- Dry Etch Equipment
- CVD Equipment
- Plasma Ashing Equipment

All trademarks and registered trademarks noted in this file are the exclusive property of Nippon Valqua Industries, Ltd. unless otherwise specified. Although these data are created based on the data and the information (Internal master file No.: VMF104-011) as of March 2011, Nippon Valqua Industries, Ltd. may change these data without notice for the reason of improvement in functional of a product, standard revision and others. Please note the following point in use of these data. (1) An operating temperature, pressure range, durability, etc. indicated in this catalogue do not assume each operation conditions but show the application possibility based on our company data, an actual result, etc. Therefore, please use these data after checking the aptitude in actual use environment. (2) The data contained within this catalogue can only be taken as a guide. (3) A standard, a value, etc. are the purposes made legible, and may be performing an extract, recombination, arrangement, conversion, etc. of a value. (4) Although the maximum attention was paid in this data creation, Nippon Valqua Industries, Ltd. will not accept responsibility for any loss incurred through error or omission. Please contact your distributor or VALQUA group if you have any questions.

© 2011 Nippon Valqua Industries, Ltd. All rights reserved.  
Products manufactured in Japan, unless otherwise specified.

20F-8, No.295, Sec.2, Gangfu  
Rd., Hsinchu City, Taiwan.  
Tel : 03-572-0467  
Fax: 03-573-7232



**TAIWAN VALQUA® ENGINEERING INTERNATIONAL, LTD.**

Version: 110324